

**DOES
EXACTLY
WHAT IT
SAYS ON
THE TIN™**

**Ronseal Promise, if you do exactly what it says on the tin,
this product will do exactly what it says on the tin.**

ULTIMATE FORMULA

+

ULTIMATE APPLICATION

=

THE PERFECT FINISH

Ronseal Perfect Finish Decking Stain

- Ultimate protection for timber decking.
- Colours, protects and waterproofs decking in one, with a beautiful, translucent finish.
- Hardwearing, scuff resistant formula that withstands foot traffic.
- Ultra tough and long lasting, resists cracking, peeling and blistering.
- Quick drying - deck rainproof in only 90 minutes.

Ronseal Perfect Finish Deck Pad

- Applies optimum film thickness to ensure ultimate protection.
- Unique foam-flock combination ensures a balanced and even application for a perfect finish.
- Long flock fibres hold more oil than a brush for greater, smoother coverage.
- Thick foam pad base ensures Deck Pad moulds itself into all the grooves.
- Unique design also avoids pooling in grooves.

Ronseal Perfect Finish Decking Stain combines the superior formula of Ronseal Decking Stain with the Perfect Finish Deck Pad to provide your deck with the ultimate colour, waterproofing and protection.

The Perfect Finish Deck Pad ensures the optimum film thickness is achieved with smooth, even coverage, delivering the ultimate protection and the Perfect Finish in one.

WHERE CAN IT BE USED?

Ronseal Decking Stain is specially formulated for use on all smooth or grooved decking timber including pre-treated, pressure treated and preservative impregnated wood. It is recommended for all exterior horizontal timber where foot traffic and wear will occur. It can be used on new wood, weathered wood, or wood which has been previously treated with a similar colour.

DRYING TIMES

Rainproof in 1½ hours - Re-coat in 4 hours.
Drying times will vary depending on climatic conditions and substrate coated. Allow 24 hours before subjecting the coating to foot traffic.

COVERAGE

This 2.5L pack is normally sufficient to coat:
Grooved boards = 10-15m² with 2 coats.
Smooth-sawn boards = 15-20m² with 2 coats.
Coverage rates may vary depending on the absorbency and profile of the wood.

PREPARATION

Only pre-treated, pressure treated or preservative impregnated timber should be used to build decking. Decking timber should be free from all dust, dirt, oil, mildew, algae and other contaminants. Remove any existing loose, flaking or peeling coatings. On pre-treated or wax coated decking timber try a small area for adhesion properties. New timber decks need to be

thoroughly prepared before treatment. Apply Ronseal Decking Cleaner & Reviver and scrub vigorously with a stiff brush to open the pores of the wood, this removes any contamination remaining from the manufacturing process. Rinse thoroughly with clean water, ideally using a pressure washer and allow to dry. Test the effectiveness of the cleaning by splashing the deck with water, if beading occurs, re-clean and retest prior to application. Colour label indicates approximate colour only. The treatment of a small test area to determine the final colour is recommended. Colour may be influenced by texture, grain, colour, porosity, type of wood and previous treatments.

APPLICATION

Apply only to dry timber. Do not apply in wet conditions or when rain is likely before the product has time to dry.

1. Remove the overcap and assemble the pad. Remove the lid, which can be used as a tray if desired. If using the lid, wash with water and detergent and dry using a clean soft cloth. Stir the stain thoroughly and then pour approximately 1 to 1.5cm into the tray. Do not dilute.
2. Dip the pad into the stain, ensuring the underside of the pad is immersed. Dip the pad evenly taking care not to overload it.
3. Starting in the furthest corner, push or pull the pad in the direction of the woodgrain. The pad will hold more product than a brush so you will be able to apply in long, smooth strokes. The pad allows you to work away

excess stain and redistribute it evenly along the decking board, avoiding puddles in the grooves.

4. When applying to deck boards, treat 3-4 boards at a time to avoid overlap marks.
5. Two coats are recommended allowing 4 hours between coats. A third coat may be applied if a deeper colour is required. For maximum protection apply to all sides and ends of the decking.
Note: If additional stain is required Ronseal Decking Stain is available in a 2.5L tin.

CLEAN UP & APPLICATOR CARE

Remove as much decking stain as possible from the pad and tray before cleaning. Clean pad and tray whilst wet with water and detergent. Always leave the pad to dry out with the flock facing upwards. Some authorities have special facilities for disposing of waste coatings. Do not empty into drains or watercourses.



EU limit value for this product
(cat A/i): 140 g/l (2007)/140g/l (2010).
This product contains max 50g/l VOC.

RONSEAL PERFECT FINISH DECKING STAIN

Use only in well-ventilated areas. Avoid contact with skin and eyes. After contact with skin, wash immediately with plenty of water. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Keep out of the reach of children. Protect from frost. Do not use below 10°C or in conditions of high humidity. Ensure container is fully resealed after use. To avoid the risk of spillage, always store and transport in a secure and upright position.

FOR FURTHER ADVICE PLEASE CONTACT:

RONSEAL TECHNICAL SERVICES,
Tel: 0114 240 9469
Ronseal Ltd, Thornciffe Park,
Chapelton, Sheffield. S35 2YP
Tel: 0114 246 7171
Fax: 0114 245 5629
enquiry@ronseal.co.uk
www.ronseal.co.uk

RONSEAL AND RONSEAL DOES EXACTLY WHAT IT SAYS ON THE TIN ARE REGISTERED TRADEMARKS OF THE SHERWIN-WILLIAMS COMPANY © 2010. MADE IN UK.

2.5 litre e